

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

Claim 1 (currently amended): A process for preparing a homopolymer or copolymer having a melt flow index (MFR 190/15) of from 1.3 g/10 min to 10 g/10 min, a molecular weight distribution  $M_w/M_n$  of from 3 to 30, a bulk density of from 0.05 g/cc to 0.4 g/cc and an average particle size of from 5  $\mu\text{m}$  to 300  $\mu\text{m}$  by polymerization of the monomers using a mixed catalyst prepared by reacting a Ti(IV) compound with an organic aluminum compound at from ~~20°C~~ -20°C to 50°C in a suspension medium for from 0.5 minute to 60 minutes.

Claim 2 (previously presented): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the melt flow index (MFR 190/15) is from 1.3 g/10 min to 10 g/10 min, the molecular weight distribution  $M_w/M_n$  is from 3 to 10, the bulk density is from 0.1 g/cc to 0.4 g/cc and the average particle size is from 20  $\mu\text{m}$  to 200  $\mu\text{m}$ .

Claim 3 (previously presented): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the melt flow index (MFR 190/15) is from 1.4 g/10 min to 5 g/10 min, the molecular weight distribution  $M_w/M_n$  is from 4 to 8, the bulk density is from 0.13 g/cc to 0.3 g/cc and the average particle size is from 60  $\mu\text{m}$  to 180  $\mu\text{m}$ .

Claim 4 (previously presented): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the melt flow index (MFR 190/15) is from 1.4 g/10 min to 3 g/10 min, the molecular weight distribution  $M_w/M_n$  is from 4 to 8, the bulk density is from 0.15 g/cc to 0.28 g/cc and the average particle size is from 60  $\mu\text{m}$  to 160  $\mu\text{m}$ .

Claim 5 (previously presented): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the polymerization is carried out at a temperature of from 30°C to 130°C and a pressure of from 0.05 MPa to 4 MPa.

Claim 6 (previously presented): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the polymerization is carried out at a temperature of from 50°C to 90°C.

Claim 7 (previously presented): The process for preparing an ethylene homopolymer or copolymer as claimed in claim 1, wherein the concentrations of the reactants in the starting solutions in the preparation of the mixed catalyst are from 0.1 mol to 9.1 mol of Ti(IV) compound/l of solvent and from 0.01 mol to 1 mol of Al compound/l.

Claim 8 (cancelled)

Claim 9 (cancelled)

Claim 10 (cancelled)

Application No.: 09/787875

Docket No.: 05587-00311-US1

Claim 11 (cancelled)

Claim 12 (cancelled)